


Technical Datasheet Homide 400L		
Document No.: TD 027 Revised: KA/AU, 04.09.2018	HOS-Technik GmbH Obersteigerweg 4 9431 St. Stefan AUSTRIA	T: +43 4352 52587 F: +43 4352 52588 hos@hos-technik.at www.hos-tec.com

Biscitraconimide resin

1. Chemical Structure:



2. Chemical Properties:

Characteristic	Specification	Method of Analysis
Form:	Viscous liquid	-
Colour:	Brown	-
Gel time:	300-900 sec	Hot plate at 171°C (+1 % DMAP)
Resin content:	68-72 %	TGA
Solvent content:	25-30 %	TGA
Polymer content:	50-70 %	GPC
Monomer content:	30-50 %	GPC

3. Handling:

Please refer to safety data sheet Homide 400L

4. Storage:

Homide 400L should be stored cool and dry at temperatures not exceeding 35°C in tightly closed containers. Under these conditions the product can be stored for a period of at least one year.