


# TECHNICAL DATASHEET

## Homide 400

HOS-Technik  
Vertriebs- und Produktions-GmbH  
Am Industriepark 5  
9431 St. Stefan, AUSTRIA  
Tel. +43/4352/52587  
Fax +43/4352/52588  
E-mail: hos@hos-technik.at  
www.hos-tec.com

Resin based on Biscitraconimide

### 1. Chemical Structure:



### 2. Chemical Properties:

Characteristic	Specification	Method of Analysis
Form:	Resolidified melt	-
Colour:	Brown	-
Gel time:	500-900 sec	Hot plate at 200°C
Softening range:	70-120°C	DSC
Polymer content:	50-70 %	GPC
Monomer content:	30-50 %	GPC

### 3. Handling:

Please refer to safety data sheet Homide 400.

### 4. Storage:

Homide 400 should be stored in a cool and dry place at temperatures below 35°C, excluding humidity, in tightly closed containers. Under these conditions the product can be stored for a period of at least two years.