



<b>Technical Datasheet</b> <b>Homide 802</b>		
Document No.: TD 030 Revised: KA/AU, 04.09.2018	HOS-Technik GmbH Obersteigerweg 4 9431 St. Stefan AUSTRIA	T: +43 4352 52587 F: +43 4352 52588 hos@hos-technik.at www.hos-tec.com

Prepolymer of bismaleimide monomers

1. Chemical Structure:



2. Chemical Properties:

Characteristic	Specification	Method of Analysis
Form:	Resolidified melt	-
Colour:	Brown	-
Gel time:	300-500	Hot plate at 171°C
Softening range:	40-70°C	DSC
Polymer content:	40-80 %	GPC
Monomer content:	20-30 %	GPC

3. Handling:

Please refer to safety data sheet Homide 802

4. Storage:

Homide 802 should be stored cool and dry at temperatures not exceeding 35°C in tightly closed containers. Under these conditions the product can be stored for a period of at least six months.