


# TECHNICAL DATASHEET

## Homide 806

HOS-Technik  
Vertriebs- und Produktions-GmbH  
Am Industriepark 5  
9431 St. Stefan, AUSTRIA  
Tel. +43/4352/52587  
E-mail: hos@hos-technik.at  
www.hos-tec.com

Eutectic blend based on aromatic and aliphatic bismaleimide monomers

### 1. Chemical Structure:



### 2. Chemical Properties:

Characteristic	Specification	Method of Analysis
Form:	Resolidified melt	-
Colour:	yellow-brown	-
Gel time:	>40 min	Hot plate at 171°C
Softening range:	110-130°C	DSC
Polymerisation onset:	200-240°C	DSC
Poymerisation max.:	230-270°C	DSC
VOC:	≤3 %	TGA



HOS-Technik

Vertriebs- und Produktions-GmbH  
Am Industriepark 5  
9431 St. Stefan, AUSTRIA  
Tel. +43/4352/52587  
E-mail: [hos@hos-technik.at](mailto:hos@hos-technik.at)  
[www.hos-tec.com](http://www.hos-tec.com)

### 3. Handling:

Please refer to safety data sheet Homide 806.

### 4. Storage:

Homide 806 should be stored in a cool and dry place at temperatures below 30°C, excluding humidity, in tightly closed containers. Under these conditions the product can be stored for a period of at least six months.

Document No.: TD 032  
Revised: KA/AU, 20.03.2023